

# CERACLEAN1P

Racle / Doctor blade



## Caratteristiche del poliuretano / poliurethane characteristics

	Um	Norme / norms	Valore / value
Colore / colour			rosso / red
Durezza / hardness	SH/A	ASTM D 2240	82
Carico di rottura / tensile strength	Mpa	ASTM D 412	25
Peso Specifico / specific weight	gr/cm <sup>3</sup>	ASTM D 1817	1,24
Allungamento a rottura / elongation at breaking	%	ASTM D 412	850
Perdita all'abrasione / abrasione loss	mm <sup>3</sup>	ASTM D 5963	35
Temperatura di esercizio / operating temperature	min. / max.		80
Resistenza all'acqua,acidi / resistance to water and acids	°C		scadente / poor
Resistenza a oli, gasolio / resistance to oil and fuel			buona / good
Impermeabilità ai gas / Impermeability to gases			buona / good
Resistenza all' ozono / resistance to ozone			eccellente / excellent

## Tabella Tolleranze / Table Tolerances

	da / from	a / to	Um	tolleranze / tolerances
Durezza / hardness	-	-	SH/A	± 5

