

# PUROUND90R10

Lastre tecniche / technical sheets



## Specifiche tecniche / technical specification

|   | Um   | Norme / norms | Valore / value |
|---|------|---------------|----------------|
| Colore / color                                  |      |               | rosso / red    |
| Durezza / hardness                              | SH/A |               | 92             |
| Carico di rottura / tensile strength            | Mpa  |               | 34,5           |
| Allungamento a rottura / elongation at break    | %    |               | 460            |
| Deformazione permanente / permanent deformation | %    |               | 5              |
| Resistenza allo strappo / tear resistance       | KN/m |               | 63,2           |
| Modulo a 100 % / form to 100%                   | Mpa  |               | 7,9            |
| Modulo a 300 % / form to 300%                   | Mpa  |               | 12,2           |

## Specifiche tecniche / technical specification

|                     | Um | Norme / norms | Valore / value |
|---------------------|----|---------------|----------------|
| Diametro / diameter | mm |               | 10             |
| Lunghezza / length  | mm |               | 300            |

Tabella Tolleranze / Table Tolerances

|                     | da / from | a / to | Um | tolleranze / tolerances |
|---------------------|-----------|--------|----|-------------------------|
| Diametro / diameter | Ø 10      | Ø 25   | mm | ± 0,5                   |
| " / "               | Ø 30      | Ø 100  | mm | ± 1,5                   |
| " / "               | Ø 120     | Ø 140  | mm | ± 2,5                   |