

PUROUND90R55

Lastre tecniche / technical sheets



Specifiche tecniche / technical specification

| | Um | Norme / norms | Valore / value |
|---|------|---------------|----------------|
| Colore / color | | | rosso / red |
| Durezza / hardness | SH/A | | 92 |
| Carico di rottura / tensile strength | Mpa | | 34,5 |
| Allungamento a rottura / elongation at break | % | | 460 |
| Deformazione permanente / permanent deformation | % | | 5 |
| Resistenza allo strappo / tear resistance | KN/m | | 63,2 |
| Modulo a 100 % / form to 100% | Mpa | | 7,9 |
| Modulo a 300 % / form to 300% | Mpa | | 12,2 |

Specifiche tecniche / technical specification

| | Um | Norme / norms | Valore / value |
|---------------------|----|---------------|----------------|
| Diametro / diameter | mm | | 55 |
| Lunghezza / length | mm | | 500 |

Tabella Tolleranze / Table Tolerances

| | da / from | a / to | Um | tolleranze / tolerances |
|---------------------|-----------|--------|----|-------------------------|
| Diametro / diameter | Ø 10 | Ø 25 | mm | ± 0,5 |
| " / " | Ø 30 | Ø 100 | mm | ± 1,5 |
| " / " | Ø 120 | Ø 140 | mm | ± 2,5 |